

## D3701 Product Data Sheet

### General Description

**D3701** is a rigid moulded friction material which is mottled slate grey in appearance; it is a non-metallic asbestos free material having a random base of synthetic fibre and uses a specially developed resin which contributes to both the strength and the performance of the material. **D3701** has moderate mechanical strength together with a medium coefficient of friction combined with a low rate of wear; it machines well and facings can be gear cut on the inside or outside circumference depending on the application. The material can also be manufactured with moulded gear teeth, if the quantities required are sufficient to justify the tooling. **D3701** is suitable for use in both dry or oil immersed applications.

### Applications

- Industrial clutches, drum and disc brakes, dry or oil immersed applications
- Band linings and segments for Automatic and Semi-Automatic transmissions

### Bonding

**D3701** may be bonded using any of the established adhesives recommended for friction material. However, to obtain the best results it is necessary to use a thermosetting adhesive. Care should be taken to ensure that the temperature to which the material is to be subjected does not exceed the recommendations of the adhesive manufacturer.

### Mating Surface

A good quality, fine grained, pearlitic cast iron or cold rolled steel with a Brinell hardness of 200. Cast steels are not recommended.

### Availability

Sheets 660 x 330mm up to 8.0mm thick  
Sheets 660 x 530mm up to 12.7mm thick  
Special shapes on request  
Discs on request

### TECHNICAL DATA

#### Friction

$\mu$ for design purposes :	Static (dry)	0.30	Static (oil)	0.08
	Dynamic (dry)	0.32	Dynamic (oil)	0.10

#### Recommended Operating Range

Pressure : Dynamic	70-700kN/m <sup>2</sup> (10-100lbf/in <sup>2</sup> )
In oil	0.2-2.1 MN/m <sup>2</sup> (30-300lbf/in <sup>2</sup> )
Max. rubbing speed	25 m/s (60 ft/s)
Max. continuous temperature	225°C
Max. intermittent temperature	225°C
Max. temperature	250°C

#### Physical Properties

Density	1.62 g/cc
Gogan Hardness	Below 25Gc
Ultimate tensile strength	29.0 MN/m <sup>2</sup> (4,206 lbf/in <sup>2</sup> )
Ultimate shear strength	27.0 MN/m <sup>2</sup> (3,924 lbf/in <sup>2</sup> )
Ultimate compressive strength	154 MN/m <sup>2</sup> (22,336 lbf/in <sup>2</sup> )
Thermal conductivity	0.529 W/m °C

(All physical properties shown above are all mean values)

The information supplied in this data sheet is believed to be accurate and reliable, and was obtained by scientific and laboratory testing. However, since actual conditions of use are largely outside the control of FEROTEC FRICTION LIMITED, it is suggested that this material be thoroughly tested and its suitability for use be determined before final acceptance.

Issue 8 Jun 10

